

PCTORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁷ : C23C 22/07	A1	(11) International Publication Number: WO 00/52227 (43) International Publication Date: 8 September 2000 (08.09.00)
<p>(21) International Application Number: PCT/US00/05458</p> <p>(22) International Filing Date: 2 March 2000 (02.03.00)</p> <p>(30) Priority Data: 11/54834 2 March 1999 (02.03.99) JP</p> <p>(71) Applicant (for all designated States except US): HENKEL CORPORATION [US/US]; Suite 200, 2500 Renaissance Boulevard, Gulph Mills, PA 19406 (US).</p> <p>(72) Inventors; and (75) Inventors/Applicants (for US only): KAWAGUCHI, Jun [JP/JP]; 3-15-16, Ryokuen, Izumi-ku, Yokohama-shi, Kanagawa 245-0002 (JP). MANMI, Tomoyuki [JP/JP]; B-1108 1379-2, Nakajima Chigasaki-shi, Kanagawa 253-0073 (JP). ISHIKURA, Kazuhiro [JP/JP]; No. III-607, 17-3, Higashinagasasa nagasasa-cho, Aichi-shi, Aichi 472-0045 (JP).</p> <p>(74) Agent: HARPER, Stephen, D.; Henkel Corporation, Suite 200, 2500 Renaissance Boulevard, Gulph Mills, PA 19406 (US).</p>		<p>(81) Designated States: AE, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CR, CU, CZ, DE, DK, DM, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, TZ, UA, UG, US, UZ, VN, YU, ZA, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SL, SZ, TZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).</p> <p>Published <i>With international search report.</i></p>
<p>(54) Title: NONSLUDGING ZINC PHOSPHATING COMPOSITION AND PROCESS</p>		
<p>(57) Abstract</p> <p>Electrolysis using a suitable electrolyte provides a completely nonsludging zinc phosphate conversion coating process that produces a high quality conversion coating in a very short time. The suitable electrolyte contains at least water, dissolved nitric acid, and dissolved zinc cations and optionally also contains m chemically distinct species of cations other than zinc and n chemically distinct species of anions other than anions derivable by ionization of phosphoric and nitric acids, each of m and n independently being zero or a positive integer. Preferably, the liquid composition contains as additive at least one selection from nitrous acid, permanganic acid, peroxysulfuric acid, hydrogen peroxide, chloric acid, perchloric acid, nitrobenzenesulfonic acid, hydroxylamine, starch/phosphoric acid esters, fluorine compounds, and salts of the preceding; and/or the metal substrate is subjected to cathodic electrolysis after the workpiece has been brought into contact with a weakly basic aqueous colloidal solution that contains titanium oxide, titanium hydroxide, and zinc phosphate.</p>		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						